

Electrical and Thermal Transport in Carbon Nanotubes

David Tománek¹

*Department of Physics and Astronomy and Center for Fundamental Materials Research,
Michigan State University, East Lansing, Michigan 48824-1116, USA*

Abstract. Owing to their atomic-level perfection, carbon nanotubes exhibit unusually high electrical and thermal conductivity. Our electrical transport calculations, performed using a scattering technique based on the Landauer-Büttiker formalism, suggest that the conductance of inhomogeneous multi-wall nanotubes may show an unusual fractional quantization behavior, in agreement with recent experimental data. Our calculations also indicate that due to the combination of a large phonon mean free path, speed of sound and specific heat, the thermal conductivity of an isolated (10, 10) carbon nanotube exceeds that of any known material, reaching the value $\lambda \approx 6,600$ W/m·K at room temperature.

Introduction

With the continually decreasing size of electronic and micromechanical devices, there is an increasing interest in materials that conduct electricity and heat efficiently. Carbon nanotubes [1], consisting of graphite layers wrapped into seamless cylinders, are now being produced routinely using carbon arc, laser vaporization of graphite, catalytic decomposition of carbon monoxide at high pressures, and chemical vapor deposition techniques [2]. These methods yield single-wall and multi-wall nanotubes that are up to a fraction of a millimeter long, yet only nanometers in diameter. Virtual absence of defects suggests that these molecular conductors should be ideal candidates for use as nano-wires that conduct electricity and heat efficiently.

The present study has been motivated by several open questions. The first relates to electron transport in nanotubes that is believed to be ballistic in nature, implying the absence of inelastic scattering. Recent conductance measurements of multi-wall carbon nanotubes [3] have raised a significant controversy due to the observation of unexpected conductance values in apparent disagreement with theoretical predictions. The second open question relates to the suitability of carbon

¹) In collaboration with Young-Kyun Kwon, Savas Berber, Stefano Sanvito, and Colin J. Lambert.

nanotubes to conduct heat efficiently in view of their atomically perfect structure and the stiffness of the interatomic bonds in self-supporting graphitic cylinders.

Electrical Conductance of Carbon Nanotubes

To address the conductance of multi-wall carbon nanotubes [4], we combined a linear combination of atomic orbitals (LCAO) Hamiltonian with a scattering technique developed recently for magnetic multilayers [5,6]. The parameterization of the LCAO matrix elements is based on *ab initio* results for simpler structures [7]. Our calculations can build on a number of published theoretical studies of the electronic structure of single-wall [8–10] and multi-wall carbon nanotubes [11–13]. Calculations for single-wall nanotube ropes [14,15] have shown that inter-wall coupling may induce pseudo-gaps near the Fermi level in these systems, with serious consequences for their conductance behavior.

Our scattering technique approach to determine the conductance of inhomogeneous multi-wall nanotubes [4] is based on the quantum-mechanical scattering matrix S of a phase-coherent “defective” region that is connected to “ideal” external reservoirs [5]. At zero temperature, the energy-dependent electrical conductance is given by the Landauer-Büttiker formula [16]

$$G(E) = \frac{2e^2}{h} T(E) , \quad (1)$$

where $T(E)$ is the total transmission coefficient, evaluated at the Fermi energy E_F .

For a homogeneous system, $T(E)$ assumes integer values corresponding to the total number of open conduction channels at the energy E . For individual (n, n) “armchair” tubes, this integer is further predicted [17] to be an even multiple of the conductance quantum $G_0 = 2e^2/h \approx (12.9 \text{ k}\Omega)^{-1}$, with a conductance $G = 2G_0$ near the Fermi level. In the $(10, 10)@(15, 15)$ double-wall nanotube [13] and the $(5, 5)@(10, 10)@(15, 15)$ triple-wall nanotube, the inter-wall interaction significantly modifies the electronic states near the Fermi level and blocks some of the conduction channels close to E_F .

The experimental set-up of Ref. [3], shown schematically in Fig. 1(a), consists of a multi-wall nanotube that is attached to a gold tip of a Scanning Tunneling Microscope (STM) and used as an electrode. The STM allows the tube to be immersed at calibrated depth intervals into liquid mercury, acting as a counter-electrode. This arrangement allows precise conduction measurements to be performed on an isolated tube. The experimental data of Ref. [3] for the conductance G as a function of the immersion depth z of the tube, reproduced in Fig. 1(e), suggest that in a finite-length multi-wall nanotube, the conductance may achieve values as small as $0.5G_0$ or $1G_0$.

As nothing is known about the internal structure of the multi-wall nanotubes used or the nature of the contact between the tube and the Au and Hg electrodes, we have considered several scenarios and concluded that the experimental data can




FIGURE 1. (a) Schematic geometry of a multi-wall nanotube that is being immersed into mercury up to different depths labeled Hg(#1), Hg(#2), and Hg(#3). Only the outermost tube is considered to be in contact with the gold STM tip on which it is suspended. The conductance of this system is given in (b) for the immersion depth Hg(#1), in (c) for Hg(#2), and in (d) for Hg(#3) as a function of the position of E_F . The Fermi level may shift with changing immersion depth within a narrow range indicated by the shaded region. (e) Conductance G of a multi-wall nanotube as a function of immersion depth z in mercury, given in units of the conductance quantum $G_0 = 2e^2/h \approx (12.9 \text{ k}\Omega)^{-1}$. Results predicted for the multi-wall nanotube, given by the dashed line, are superimposed on the experimental data of Ref. [3]. The main figure and the inset show data for two nanotube samples, which in our interpretation only differ in the length of the terminating single-wall segment. From Ref. [4], ©American Physical Society 2000.

only be explained by assuming that the current injection from the gold electrode occurs exclusively into the outermost tube wall, and that the chemical potential equals that of mercury, shifted by a contact potential, only within the submerged portion of the tube. In other words, the number of tube walls in contact with mercury depends on the immersion depth. The main origin of the anomalous conductance reduction from the theoretically expected integer multiple of $2G_0$ is the backscattering of carriers at the interface of two regions with different numbers of walls due to a discontinuous change of the conduction current distribution across the individual walls.

Thermal Conductivity of Carbon Nanotubes

To address the thermal conductivity of carbon nanotubes as a function of temperature [18], we made use of accurate carbon potentials [19] in equilibrium and non-equilibrium molecular dynamics simulations. The thermal conductivity λ of a solid along a particular direction, taken here as the z axis, is related to the heat flowing down a long rod with a temperature gradient dT/dz by

$$\frac{1}{A} \frac{dQ}{dt} = -\lambda \frac{dT}{dz}, \quad (2)$$

where dQ is the energy transmitted across the area A in the time interval dt . In systems where the phonon contribution to the heat conductance dominates, λ is proportional to Cvl , the product of the heat capacity per unit volume C , the speed of sound v , and the phonon mean free path l . Due to a virtual absence of atomic-scale defects, we expect l to be unusually large in carbon nanotubes. Also the heat capacity and speed of sound are expected to equal or even exceed those of diamond, which is known to have the highest measured thermal conductivity when isotopically pure. Hence, we suspect that isolated carbon nanotubes may be Nature's best heat conductors.

Precise measurements of thermal conductivity are very difficult, as witnessed by the reported thermal conductivity data in the basal plane of graphite [20] which show a scatter by nearly two orders of magnitude. Similar uncertainties have been associated with thermal conductivity measurements in "mats" of nanotubes [21].

Theoretical prediction of the thermal conductivity have proven equally challenging, albeit for different reasons. In a direct molecular dynamics simulation, construction of a periodic array of hot and cold regions along a nanotube introduces extra scattering centers that limit the phonon mean free path to below the size of the unit cell, thus significantly reducing the value of λ . Equilibrium molecular dynamics simulations based on the Green-Kubo formula, which relate λ to the integral over time t of the heat flux autocorrelation function, converge very slowly and require extensive ensemble averaging. We found that the most suitable approach to determine thermal conductivity in nanotubes combines the Green-Kubo formula with nonequilibrium thermodynamics [22,23].




FIGURE 2. Temperature dependence of the thermal conductivity λ for a (10,10) carbon nanotube for temperatures below 400 K. From Ref. [18], ©American Physical Society 2000.

Results of nonequilibrium molecular dynamics simulations for the thermal con-

ductance of an isolated (10, 10) nanotube aligned along the z axis are presented in Fig. 2. We find that at low temperatures, when l is nearly constant, the temperature dependence of λ follows that of the specific heat. At high temperatures, where the specific heat is constant, λ decreases as the phonon mean free path becomes smaller due to umklapp processes. Our calculations suggest that at $T = 100$ K, carbon nanotubes show an unusually high thermal conductivity value of 37,000 W/m·K. This value lies very close to the highest value observed in any solid, $\lambda = 41,000$ W/m·K, that has been reported [24] for a 99.9% pure ^{12}C crystal at 104 K. In spite of the decrease of λ above 100 K, the room temperature value of 6,600 W/m·K is still very high, twice the reported thermal conductivity value of 3,320 W/m·K for nearly isotopically pure diamond [25]. We also found this value to lie close to that of a hypothetical graphene monolayer. In graphite, we find that the inter-layer interaction reduces λ by one order of magnitude due to the reduced phonon mean free path. Similarly, we expect the high thermal conductivity value predicted for an isolated nanotube to decrease upon contact with a surrounding matrix, such as a nanotube “rope”.

Summary and Conclusions

The calculations discussed above indicate that carbon nanotubes show unusual electrical and thermal conductance behavior. Results for the electrical transport indicate that the inter-wall interaction in multi-wall nanotubes not only blocks certain conduction channels, but also re-distributes the current non-uniformly across the walls. The puzzling observation of fractional quantum conductance in multi-wall nanotubes can be explained by back-scattering at the interfaces of regions with different numbers of walls. Sample-to-sample variations in the internal structure of the tubes offer a natural explanation for the observed variations of the conductance. Nonequilibrium molecular dynamics simulations suggest that carbon nanotubes may conduct heat exceptionally well, owing to a combination of a large phonon mean free path, high speed of sound and specific heat. The predicted thermal conductivity value $\lambda \approx 6,600$ W/m·K for an isolated (10, 10) carbon nanotube at room temperature is twice that of isotopically pure diamond, Nature’s best heat conductor.

Acknowledgment

The author gratefully acknowledges financial support by the organizers of the “International Winter School on Electronic Properties of Novel Materials: Molecular Nanostructures” (IWEPNM’2000) in Kirchberg (Austria), March 4-11, 2000, and by the Office of Naval Research and DARPA under Grant Number N00014-99-1-0252.

REFERENCES

1. S. Iijima, *Nature* **354**, 56 (1991).
2. M.S. Dresselhaus, G. Dresselhaus, and P.C. Eklund, *Science of Fullerenes and Carbon Nanotubes* (Academic Press, San Diego, 1996).
3. S. Frank, P. Poncharal, Z.L. Wang, and W.A. de Heer, *Science* **280**, 1744 (1998).
4. Stefano Sanvito, Young-Kyun Kwon, David Tománek, and Colin J. Lambert, *Phys. Rev. Lett.* **84**, 1974 (2000).
5. S. Sanvito, C.J. Lambert, J.H. Jefferson, and A.M. Bratkovsky, *Phys. Rev. B* **59**, 11936 (1999).
6. S. Sanvito C.J. Lambert, J.H. Jefferson, and A.M. Bratkovsky, *J. Phys. C: Condens. Matter.* **10**, L691 (1998).
7. D. Tománek and M.A. Schluter, *Phys. Rev. Lett.* **67**, 2331 (1991).
8. J.W. Mintmire, B.I. Dunlap, and C.T. White, *Phys. Rev. Lett.* **68**, 631 (1992).
9. R. Saito, M. Fujita, G. Dresselhaus, and M.S. Dresselhaus, *Appl. Phys. Lett.* **60**, 2204 (1992).
10. N. Hamada, S. Sawada, and A. Oshiyama, *Phys. Rev. Lett.* **68**, 1579 (1992).
11. R. Saito, G. Dresselhaus, and M.S. Dresselhaus, *J. Appl. Phys.* **73**, 494 (1993).
12. Ph. Lambin, L. Philippe, J.C. Charlier, and J.P. Michenaud, *Comput. Mater. Sci.* **2**, 350 (1994).
13. Y.-K. Kwon and D. Tománek, *Phys. Rev. B* **58**, R16001 (1998).
14. P. Delaney, H.J. Choi, J. Ihm, S.G. Louie, and M.L. Cohen, *Nature* **391**, 466 (1998).
15. Y.-K. Kwon, S. Saito, and D. Tománek, *Phys. Rev. B* **58**, R13314 (1998).
16. M. Büttiker, Y. Imry, R. Landauer, and S. Pinhas, *Phys. Rev. B* **31**, 6207 (1985).
17. L. Chico, L.X. Benedict, S.G. Louie and M.L. Cohen, *Phys. Rev. B* **54**, 2600 (1996), W. Tian and S. Datta, *ibid.* **49**, 5097 (1994), M.F. Lin and K.W.-K. Shung, *ibid.* **51**, 7592 (1995).
18. Savas Berber, Young-Kyun Kwon, and David Tománek, *Phys. Rev. Lett.* **84** (2000).
19. J. Tersoff, *Phys. Rev. B* **37**, 6991 (1988).
20. Citrad Uher, in *Landolt-Börnstein*, New Series, III **15c** (Springer-Verlag, Berlin, 1985), pp. 426–448.
21. J. Hone, M. Whitney, A. Zettl, *Synthetic Metals* **103**, 2498 (1999).
22. D.J. Evans, *Phys. Lett.* **91A**, 457 (1982).
23. D.P. Hansen and D.J. Evans, *Molecular Physics* **81**, 767 (1994).
24. Lanhua Wei, P.K. Kuo, R.L. Thomas, T.R. Anthony, and W.F. Banholzer, *Phys. Rev. Lett.* **70**, 3764 (1993).
25. T.R. Anthony, W.F. Banholzer, J.F. Fleischer, Lanhua Wei, P.K. Kuo, R.L. Thomas, and R.W. Pryor, *Phys. Rev. B* **42**, 1104 (1990).